

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : A61K 9/00, 9/16, 38/28, 38/46, 38/48, 38/06</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/00176 (43) International Publication Date: 6 January 2000 (06.01.00)</p>
<p>(21) International Application Number: PCT/GB99/02023 (22) International Filing Date: 28 June 1999 (28.06.99) (30) Priority Data: 9814172.4 30 June 1998 (30.06.98) GB (71) Applicant: QUADRANT HEALTHCARE (UK) LIMITED [GB/GB]; 1 Mere Way, Ruddington, Nottingham NG11 6JS (GB). (72) Inventors: ROBINSON, Stuart; 15 Heckadeck Lane, Nether Broughton, Melton Mowbray LE14 3EZ (GB). SMITH, Susan, Stewart; 3 Carrington Street, Loughborough, Leicestershire LE77 0NF (GB). (74) Agent: GILL JENNINGS & EVERY; Broadgate House, 7 Eldon Street, London EC2M 7LH (GB).</p>	<p>(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).</p> <p>Published <i>With international search report.</i></p>	
<p>(54) Title: MICROPARTICLE FORMULATION FOR INHALATION</p> <p>(57) Abstract</p> <p>Microparticles, obtainable by spray-drying a substantially pure solution of a therapeutic agent, consist essentially of the agent having its therapeutic activity when administered to the lung. In a preferred embodiment the agent is insulin.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

MICROPARTICLE FORMULATION FOR INHALATION

Field of the Invention

This invention relates to a formulation of a therapeutic agent such as insulin, that is suitable for administration to the lung, and that has good stability.

5 Background of the Invention

There is now widespread interest in the formulation of therapeutic agents for inhalation. In particular, many efforts have been made to formulate suitable therapeutic agents as dry powders for delivery via inhalers.

Typically, the formulations are produced by drying the active agent in the presence of certain excipients, such as polysaccharides or citrate, to enhance stability during the drying process or in storage.

Insulin is a typical example of a therapeutic agent that can be administered to the lung, by inhalation. As a commercial product, insulin is generally provided in suspension or a solution of low concentration, as a hexamer complexed with zinc. Refrigeration is necessary, in order to maintain the stability of such a formulation. Crystalline Zn insulin is stable at neutral pH. The dry powder also requires refrigeration.

CA-A-2136704 discloses a product obtained by spray-drying a medicinal substance such as insulin (among many others) and a carrier. Example 4 discloses spray-drying a clear solution of human insulin, soya bean lecithin and lactose.

20 WO-A-9735562 again discloses spray-drying a solution of insulin and a polysaccharide. The aim of this combination is to achieve the preferred size range of spray-dried microparticles, for good lung deposition. In Examples 1 and 3, the insulin solution for spray-drying, prior to combination with polysaccharide, is prepared by dissolving zinc insulin in HCl, and then adding NaOH, to pH 7.2. The solutions for spray-drying respectively contain 25 and 6 mg/ml insulin and at least 5.5/7.2% NaCl, based on the combined weight of insulin plus salt.

30 WO-A-9524183 is directed primarily to a dry powder that comprises insulin and a carrier material, typically a saccharide, in the form of an amorphous powder of microparticles obtained by spray-drying. In addition, the Experimental section compares the properties of such microparticles with and without a saccharide excipient. The insulin solution for spray-drying is prepared by dissolving Zn-insulin in citrate buffer, to pH 6.7

± 0.3, to a solids content of 7.5 mg/ml. The powder is held in a container at 10% RH. The formulation without saccharide has considerably lower bioavailability than those with saccharide. For various reasons, this experiment cannot be reproduced: citrate is a buffer at pH 3.0-6.2, and not at pH 6.7; crystalline insulin will not dissolve in pH 6.2 citrate buffer before or after adjustment to pH 7.4 with NaOH; in any case, no alkali addition is specified.

The presence of citrate in dry powder formulations was believed to be necessary to enhance the stability of the final product (Drug Development and Industrial Pharmacy 1984; 10(3):425-451). However, in many cases, the high citrate concentration dilutes the amount of active agent in the initial feedstock, resulting in low amounts of active for drying.

Pikal and Rigsbee, Pharm. Rev. 14(10):1379-87 (1997), report that freeze-dried amorphous insulin was significantly more stable than crystalline insulin at corresponding water contents from 0 to 15% w/w. The mechanism was unclear, but may have been due to configurational differences between the amorphous and crystalline states, the reactive parts of the protein being in closer proximity in the latter. The formulation reported by Pikal and Rigsbee contains no salt, because such low concentrations of insulin (c. 0.5% w/v) are used that manipulation of the pH is unnecessary.

WO95/23613 discloses a spray-dried DNase formulation. The spray-dried product is in a crystalline form, due primarily to a high concentration of salt. It is stated that high concentrations of salt increases the dispersibility qualities of the final product. In Example 1, the final product contains 60% salt compared with 30% of the DNase.

In summary, the prior art discloses various results of interest but of uncertain commercial significance. None of the procedures described above gives a pure insulin product that is stable, or uses a sufficiently concentrated solution for spray-drying, to be suitable as a commercial procedure. The most effective procedures invariably suggest that co-spray-drying of insulin and, say, a saccharide is necessary for best results.

Summary of the Invention

The present invention is based on the surprising discovery that it is possible to spray-dry a therapeutic agent at higher (and therefore commercially useful) concentrations than have been used previously, without the concomitant production of

an undesirable high concentration of salt or other excipients. Such formulations show no substantial loss of activity after the drying process and have extended stability, by comparison with pre-spray-dried preparations. This discovery is of value for all therapeutic agents, in particular proteins and peptides to be administered via the lung.

5 According to the present invention, microparticles, obtainable by spray-drying a substantially pure solution of a therapeutic agent, consist essentially only of the agent. In a preferred embodiment, the microparticles consist essentially only of insulin and NaCl salt. Such microparticles may be held in a container at greater than 10% RH, and thus essentially at ambient humidity. The insulin microparticles are obtainable by dissolving
10 Zn-insulin in acid, adding alkali to give an insulin solution, e.g. to a pH above 7, and spray-drying the insulin solution (which also contains a salt formed as a result of the dissolution process, or a buffer).

Preferably, the microparticles are non-crystalline/amorphous.

Description of the Invention

15 As indicated above, microparticles of the invention "consist essentially" of the therapeutic agent. This term is used herein to indicate that they are substantially free of polysaccharide, or buffer salt, e.g. citrate, since none is necessary. In general, there will be no polysaccharide present at all, although an amount of up to, say 10% by weight may be tolerated. The absence of polysaccharide has the advantage that a given unit dosage,
20 e.g. a particle, contains essentially only the intended active component. This is an important consideration, for a drug that may be required in large amounts. Another advantage is the avoidance of delivering unnecessary material to a subject. A further advantage is that consistent dosing of the therapeutic agent is facilitated; this is especially important where there is a narrow therapeutic window.

25 The absence of buffer salt is desirable as it allows a more concentrated feedstock solution of the active agent to be spray-dried resulting in significant cost savings and providing a more commercial-scale process to be adopted.

30 The term "substantially pure" is used herein to indicate that the feedstock solution to be spray-dried comprises primarily only therapeutic agent and solvent. Again, as described above, there may be a minor amount of solids other than the active agent, but this has no significant effect on the eventual stability of the product.

Insulin microparticles of the invention may include components that are produced during the successive addition of acid and alkali, in preparation of the feedstock, e.g. a salt. For example, NaCl is formed if the acid and alkali are respectively HCl and NaOH. It has been found that the presence of NaCl apparently has no stabilising effect. Indeed, stability may be greater with reduced amounts of salt, again allowing a more concentrated feedstock to be used.

Typically, the solution for spray-drying may contain less than 4% by weight of salt, by weight of total solids. The salt content is based on theoretical considerations, by titration to pH 7. More particularly, this value is calculated by consideration of the molar quantities of the ions added during dissolution. The solution may contain any desired amount of the therapeutic agent, e.g. more than 20, 30 or 50 mg/ml, often up to 100 or 200 mg/ml.

As indicated above, successive addition of acid and alkali apparently destroys the crystalline form of Zn insulin. Zn may dissociate from the hexameric complex but need not be removed. Accordingly, Zn may be present in the microparticles. If desired, this or any other component, other than the therapeutic agent, may be removed, using any suitable technique known to those of skill in the art. In a preferred embodiment for insulin, the Zn is removed from solution prior to spray-drying. This may be achieved by diafiltering the solution according to methods known in the art. The Zn-free insulin may have greater stability than the Zn-containing product. Moisture may also be present.

As disclosed in more detail in WO-A-9218164, WO-A-9408627 and other Andaris publications, the conditions of spray-drying can be controlled so that microparticles having a defined size range, e.g. 0.1 to 50 μm , can be obtained. The mass median particle size is preferably 1 to 10 μm , when the product is intended for administration by inhalation.

The microparticles (microcapsules) obtained by spray-drying may be solid or hollow. Further, the surface may be smooth or "dimpled"; a dimpled surface may be beneficial for inhalation.

The microparticles have good stability and may be maintained as such, i.e. as a dry powder, in a container. During storage or in formulation, they may be mixed with any suitable pharmaceutical agents, carriers, bulking agents etc, and they may be

processed by any technique desired to give a product having the properties intended for the ultimate therapeutic use. In particular, the formulation of particles for formulations that can be delivered to the lung, e.g. using a metered dose or dry powder inhaler, are known to those skilled in the art.

5 The nature of the container is not critical. For example, it may be a glass jar or plastics box. It merely defines a storage environment within which, unlike the prior art and as evidenced below, there is no need to remove moisture or otherwise to control the conditions.

10 The therapeutic agent may be any protein or peptide having a desired therapeutic effect. Included within the definition of proteins and peptides are functional derivatives, such as glycoproteins. Typical examples of proteins that may be used include enzymes, hormones and blood plasma products. DNase and trypsin are specific examples. Others include growth hormone, calcitonins, interferons, interleukin-1 receptor and low molecular weight heparin.

15 The therapeutic agent may in particular be any of those described in WO-A-9632149. Insulin that is used in the invention may be of any suitable form. It may be, for example, bovine or human insulin. Results that have been obtained, regarding the stability of bovine insulin, apparently apply also to human insulin.

The following Examples illustrate the invention.

20 Example 1

A solution of bovine or human insulin for spray-drying is typically prepared in the following way: 5 g insulin is dissolved in 70 ml 0.05 M HCl, after which the solution is back-titrated with sufficient 1M NaOH to reform a solution from the isoelectric point precipitate. According to the final concentration required, water is added to make to
25 volume. Approximately 4.8 ml 1M NaOH is required, in this Example. The solution is then spray-dried using a Mini spray drier with an outlet temperature of approximately 87°C and a solution feed rate of approximately 0.75 g/min.

Reverse Phase High Performance Liquid Chromatography (RP-HPLC) was used to assess the stability of insulin, under the following conditions:

Column: Vydac C-18, 5 μ m, 30 nm
 Mobile Phase: A- 0.1%TFA in water
 B- 0.1% TFA in acetonitrile (95%) and water (5%)
 Gradient Elution
 5 Flow Rate: 1.5mL/min
 Detection: UV at 220nm
 Injection Volume: 100 μ L

Under these conditions, bovine insulin has a retention time of approximately 7.4 minutes.

10 A peak attributable to deamidated insulin is located at the tailing edge of the main peak. The extent of deamidation is used to indicate stability and is calculated by expressing the area of the deamidation peak as a percentage of the total peak area. Total degradation is expressed as the area of all degradant peaks as a percentage of the total peak area.

15

Table 1

Percentage Total Degradation and Deamidation of Non-Spray Dried Bovine
 Crystalline Insulin

20

Time	2°C/Ambient RH		30°C/60% RH	
	% Deamidation	% Degradation	% Deamidation	% Degradation
Initial	3.2	3.6	3.2	3.6
1 month	3.5	3.9	4.2	5.3
3 months	4.4	5.6	5.8	11.0
6 months	3.4	4.5	6.7	13.7

25

Table 2
Percentage Total Degradation and Deamidation of Insulin
Microparticles

Time	2°C/Ambient RH		30°C/60% RH	
	% Deamidation	% Degradation	% Deamidation	% Degradation
Initial	2.4	3.1	2.4	3.1
1 month	2.8	3.9	3.1	4.6
3 months	2.0	2.7	2.6	4.1
6 months	1.9	3.0	2.8	5.0

The results indicate that the extent of both deamidation and total degradation is increased with time, for all the batches evaluated. Additionally, the data suggest that spray drying appears to confer additional stability to the protein, in that the bovine crystalline insulin control suffers increased degradation in comparison to the microparticle formulations at comparable timepoints after storage at 30°C/60% RH.

To investigate whether this was also seen with human insulin, human insulin microparticles were prepared (by the same general procedure as that described above) and placed on accelerated stability at 40°C/75% RH. All samples were analysed by RP-HPLC at the initial time point, and also after 1 week, 2 weeks and 5 weeks.

Table 3
Effect of Storage at 40°C/75% RH on the Deamidation and Total
Degradation Levels of Human Insulin Recombinant From E. Coli

Storage Time at 40°C/75% RH	% Deamidation	% Total Degradation
0	0.59	0.75
1	1.57	4.27
2	1.62	5.15
5	2.37	8.40

Table 4
Effect of Storage at 40°C/75% RH on the Deamidation and Total
Degradation Levels of Human Insulin Microparticles

5

Storage Time at 40°C/75% RH	% Deamidation	% Total Degradation
0	0.95	1.65
1	1.08	2.20
2	1.03	3.10
5	1.21	3.32

10

Comparing Tables 3 and 4, the microparticle formulation of human insulin is less prone to degradation, showing only 3.32% total degradation after 5 weeks at 40°C/75% RH compared to 8.40% total degradation for the material stored as received under the same conditions.

15

Example 2

A solution of bovine DNase (molecular mass 31 kD) for spray-drying was prepared by dissolving the source material in water containing 1mM phenylmethylsulphonyl fluoride (PMSF). The PMSF is present to inhibit proteolytic degradation. The resulting feedstock solution comprised 50 mg/ml DNase.

20

The solution was then spray-dried using a Mini spray drier with an inlet temperature of 130°C, an outlet temperature of 85°C and a solution feed rate of approximately 0.8 ml/min. The activity was measured by the rate of increase of spectrophotometric absorbance at 260 nm of DNA (hyperchromicity assay), and HPLC gel permeation chromatography was used to assess the physical stability.

25

Spray-dried DNase retained approximately 90% of its initial activity and showed no change in physical stability. For spray-dried material stored at 40°C/75% RH and 25°C/60% RH, and source material stored at 25°C/60% RH, there was comparable activity and physical stability at 4 and 8 weeks.

30

Example 3

A solution of bovine trypsin (molecular mass 23.3 kD) for spray-drying was prepared by dissolving the source material (crystallised) in water. The resulting feedstock solution comprised 50 mg/ml trypsin.

5 The solution was then spray-dried as described in Example 2. Activity was measured against azocasein substrate, and HPLC gel permeation chromatography was used to assess the physical stability.

 Spray-dried trypsin retained approximately 100% of its initial activity and showed no change in physical stability. A comparison of spray-dried material stored at 4°C, 10 25°C/60% RH and 40°C/75% RH, and source material stored at 25°C/60% RH, showed substantially no loss in activity or physical stability at 12 weeks.

Example 4

 A solution of reduced glutathione (a peptide of molecular mass 307D) for spray-drying was prepared by dissolving the crystalline source material in water. The resulting 15 feedstock solution comprised 100 mg/ml reduced glutathione.

 The solution was spray-dried using a Buchi Mini B-191 spray-drier with an inlet temperature of 100°C, an outlet temperature of 74°C, and a solution feed-rate of approximately 1 ml/min. Spray-drying using either compressed air or nitrogen for atomisation of the fluid stream did not result in a significant increase in the level of 20 oxidised glutathione (initially present at 0.8% w/w, increasing to 0.9% w/w).

CLAIMS

1. Microparticles, obtainable by spray-drying a substantially pure solution of a therapeutic agent, wherein the microcapsules consist essentially only of the therapeutic agent having its therapeutic activity when administered to the lung.
- 5 2. Microparticles according to claim 1, wherein the agent is non-crystalline/amorphous.
3. Microparticles according to claim 1 or claim 2, wherein the therapeutic agent is a protein or peptide.
4. Microparticles according to any preceding claim, wherein the agent is insulin.
- 10 5. Microparticles according to any of claims 1 to 3, wherein the agent is DNase.
6. Microparticles according to any of claims 1 to 3, wherein the agent is trypsin.
7. Microparticles according to any preceding claim, consisting essentially of the agent and a salt formed in dissolution of the agent.
8. Microparticles according to claim 7, wherein the salt is formed from an alkali and
15 a mineral acid.
9. Microparticles according to any preceding claim, wherein the microparticles comprise less than 4 % salt by weight of total solids.
10. A closed container containing, at ambient humidity, microparticles according to any preceding claim.
- 20 11. An inhaler device comprising microparticles according to any of claims 1 to 9.
12. A process for the preparation of microparticles according to any of claims 1 to 9, which comprises spray-drying a substantially pure solution of a therapeutic agent.
13. A process according to claim 12, wherein the solution contains more than 10 mg/ml of agent.
- 25 14. A process according to claim 13, wherein the solution contains 20 to 200 mg/ml agent.
15. A process according to claim 13, wherein the solution contains 50 to 100 mg/ml agent.
16. A process according to any of claims 12 to 15, wherein the solution contains less
30 than 4% salt.
17. A process according to any of claims 12 to 16, wherein the solution is free of buffer salt.

18. A process according to any of claims 12 to 17, wherein the agent is insulin and the solution is obtainable by dissolving Zn-insulin in acid, and then adding alkali.
19. A process according to claim 18, wherein the Zn is removed from solution prior to spray-drying.

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 99/02023

A. CLASSIFICATION OF SUBJECT MATTER IPC 7 A61K9/00 A61K9/16 A61K38/28 A61K38/46 A61K38/48 A61K38/06		
According to International Patent Classification (IPC) or to both national classification and IPC		
B. FIELDS SEARCHED Minimum documentation searched (classification system followed by classification symbols) IPC 7 A61K		
Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched		
Electronic data base consulted during the international search (name of data base and, where practical, search terms used)		
C. DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 95 24183 A (INHALE THERAPEUTIC SYST) 14 September 1995 (1995-09-14) cited in the application page 5, line 1 -page 6, line 9 page 9, line 20 -page 10, line 15 page 12, line 27 -page 13, line 13; figures 1,2 page 14, line 1 - line 24 page 18, line 12 -page 21, line 22; figures 3A,3B; tables 1-3 claims 15-25 --- -/--	1-4,7,8, 11-13
<input checked="" type="checkbox"/> Further documents are listed in the continuation of box C.		
<input checked="" type="checkbox"/> Patent family members are listed in annex.		
* Special categories of cited documents :		
A document defining the general state of the art which is not considered to be of particular relevance *E* earlier document but published on or after the international filing date *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified) *O* document referring to an oral disclosure, use, exhibition or other means *P* document published prior to the international filing date but later than the priority date claimed *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention *X* document of particular relevance: the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone *Y* document of particular relevance: the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art. *B* document member of the same patent family		
Date of the actual completion of the international search 5 October 1999		Date of mailing of the international search report 18/10/1999
Name and mailing address of the ISA European Patent Office, P.B. 5818 Patentlaan 2 NL - 2280 HV Rijswijk Tel. (+31-70) 340-2040. Tx. 31 651 epo nl. Fax: (+31-70) 340-3016		Authorized officer Epskamp, S

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 99/02023

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 0 542 314 A (UNIV PRINCETON) 19 May 1993 (1993-05-19) column 1, line 1 - line 3 column 5, line 25 - line 36 column 2, line 31 - line 58; figures 1-6; examples 1,2 claims	1-4,9
X	YEO, SANG-DO ET AL.: "Formation of Microparticulate Protein Powders Using a Supercritical Fluid Antisolvent" BIOTECHNOLOGY AND BIOENGINEERING, vol. 41, no. 3, 5 February 1993 (1993-02-05), pages 341-346, XP002116795 ISSN: 0006-3592 Introduction Materials and Methods; figure 2 Results and Discussion; figures 1, 3-6; table 1	1-4,9
P,X	FORBES R T ET AL: "WATER VAPOR SORPTION STUDIES ON THE PHYSICAL STABILITY OF A SERIES OF SPRAY-DRIED PROTEIN/SUGAR POWDERS FOR INHALATION" JOURNAL OF PHARMACEUTICAL SCIENCES, vol. 87, no. 11, 1 November 1998 (1998-11-01), pages 1316-1321, XP000783384 ISSN: 0022-3549 Introduction Experimental Section: Materials, Spray-Drying Table 1 Results and Discussion: Particulate Properties Conclusions	1-4, 10-14,16
X	WO 95 23613 A (GENENTECH INC) 8 September 1995 (1995-09-08) cited in the application page 5, line 20 -page 6, line 2 page 7, line 14 -page 8, line 2 page 8, line 9 -page 9, line 23; figures; examples 1,2; tables A,1,2,3,5,	1-3,5, 7-17
X	US 3 515 642 A (MIMA HIROYUKI ET AL) 2 June 1970 (1970-06-02) column 2, line 8 - line 64; examples 1,5,6	1,3,6,12
	-/--	

INTERNATIONAL SEARCH REPORT

International Application No
PCT/GB 99/02023

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DE 12 27 855 B (ICHTHYOL-GESELLSHAFT, CORDES, HERMANNI & CO.) 3 November 1966 (1966-11-03) column 3, line 5 - line 21 column 4, line 13 - line 18 examples 4,5	1-3,6,12
A	----- CHEMICAL ABSTRACTS, vol. 93, no. 2, 14 July 1980 (1980-07-14) Columbus, Ohio, US; abstract no. 13123, VEBER, PAVEL ET AL: "Preparations releasing cells from animal tissues or surfaces of cultivation vessels" XP002116796 abstract & CS 180 896 B (CZECH.) 15 September 1979 (1979-09-15) -----	1-3,6,12

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/GB 99/02023

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9524183 A	14-09-1995	AU 689217 B	26-03-1998
		AU 1744995 A	25-09-1995
		BR 9507023 A	23-09-1997
		CA 2183577 A	14-09-1995
		CN 1152867 A	25-06-1997
		CZ 9602600 A	16-04-1997
		EP 0748213 A	18-12-1996
		FI 963468 A	04-09-1996
		HU 75676 A	28-05-1997
		JP 10501519 T	10-02-1998
		NO 963745 A	06-11-1996
		NZ 281112 A	27-04-1998
		PL 316199 A	23-12-1996
		ZA 9501883 A	14-12-1995
EP 0542314 A	19-05-1993	AT 167870 T	15-07-1998
		AU 668367 B	02-05-1996
		AU 2831092 A	20-05-1993
		CA 2083027 A	15-05-1993
		DE 69226064 D	06-08-1998
		DE 69226064 T	29-10-1998
		ES 2118778 T	01-10-1998
		JP 5293361 A	09-11-1993
WO 9523613 A	08-09-1995	CA 2184582 A	08-09-1995
		EP 0748225 A	18-12-1996
		JP 9509927 T	07-10-1997
US 3515642 A	02-06-1970	DE 1517787 A	29-01-1970
DE 1227855 B		NONE	
CS 180896 B	28-02-1978	NONE	